

HEAT-SHRINKABLE TUBING

HTS-W5B11 (3x)

SUMITUBE®, Made of Polyolefin, Inside adhesive, Thin-walled, Flexible, Cost effective



Highlights

- Operating temperature - 55 °C to 110 °C
- Inexpensive heat shrink tubing with excellent sealing due to inside adhesive
- Self-extinguishing
- High shrink rate 3:1
- Shrink temperature 110 °C
- RoHS and REACH conform

Dimensions

Art.-No.	Before Shrinkage (mm)		After Shrinkage (mm)		Cut Lengths (m)	Standard Packaging	
	Size	Inner Diameter (min)	Inner Diameter (max.)	Wall Thickness (nom.)		Unit Quantity (m)	Box (m)
Z85510	3/1	3.20	1.00	0.96	1.20	60	600
Z85511	4.5/1.5	4.80	1.50	1.10	1.20	60	300
Z85512	6/2	6.40	2.00	1.20	1.20	60	300
Z85513	9/3	9.50	3.00	1.30	1.20	30	150
Z85514	12/4	12.70	4.00	1.40	1.20	30	150
Z85515	19/6	19.00	6.00	1.80	1.20	18	90
Z85516	24/8	25.40	8.00	2.50	1.20	18	90
Z85517	40/13	40.00	13.00	2.50	1.20	6	24

Rolled products on request!

Created by: VS 20.11.2020

We reserve the right to make product changes.

**RELIABLE, FLEXIBLE,
CUSTOMER-ORIENTED**

HEINRICH THULESIUS GMBH & CO. KG
Zum Panrepel 15, D-28307 Bremen, GERMANY



SERVICE

Tel: +49 (0) 421-4895-0
Fax: +49 (0) 421-4895-225
E-Mail: info@thulesius.de
www.thulesius.de

**SUMITOMO
ELECTRIC
GROUP**

HEAT-SHRINKABLE TUBING

HTS-W5B11 (3x)

SUMITUBE®, Made of Polyolefin, Inside adhesive, Thin-walled, Flexible, Cost effective

Technical characteristics

Property	Test	Inspection Requirements	Typical Values
Physical	Longitudinal change by shrinking	SAE-AS23053, 5% to -15%	7%
	Tensile strength	ASTM D 792, nom. 1.10	Passed
	Elongation at break	ASTM D 638, min. 10.4 MPa	≥ 16 MPa
	Secant modulus	ASTM D 638, min. 200%	≥ 350%
	Longitudinal change by shrinking	ASTM D 882, max. 173 MPa	65 MPa
Thermal	Operating temperature		-55 °C to 110 °C
	Min. Shrink Temperature	For complete shrinkage	110 °C
	Heat shock (225°C x 4h)	SAE-AS23053, no cracking, flowing or dripping of the hose cover	Passed
	Elongation after thermal aging (175 °C x 168 h)	SAE-AS23053, min. 100%	220%
	Cold impact strength (-55 °C)	SAE-AS23053, no cracks	Passed
	Copper corrosion (121 °C x 16 h)	SAE-AS23053, no corrosion	Passed
Chemical	Colour stability (175 °C x 24 h)	SAE-AS23053, no change	Passed
	Flammability	ASTM D 2671 (B), max. 60 sec.	Passed
Electrical	Water absorption	ASTM F 570, max. 1.0%	0.3%
	Nominal voltage		600V
	Breakdown test (2.5kV x 60 sec.)	UL224, no breakdown	Passed
	Volume resistance	ASTM D 876, min. 10 ¹² Ω/cm	>10 ¹³ Ω/cm
	Dielectric strength	ASTM D 876, min. 11.8kV/mm	≥ 20 kV/mm

Created by: VS 20.11.2020

We reserve the right to make product changes.

**RELIABLE, FLEXIBLE,
CUSTOMER-ORIENTED**

HEINRICH THULESIUS GMBH & CO. KG
Zum Panrepel 15, D-28307 Bremen, GERMANY



SERVICE

Tel: +49 (0) 421-48 95-0
Fax: +49 (0) 421-48 95-225
E-Mail: info@thulesius.de
www.thulesius.de

**SUMITOMO
ELECTRIC
GROUP**